AW.FLYER (Group2)

Seating Fabrics

kreateplus.com


KREATE+

designed by technology

OUR STORY

KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS


AW.FLYER




AW FLYER-31_E4J5



AW FLYER-31_E4G1




AW FLYER-31_E4G1-1



AW FLYER-31_N8V4



AW FLYER-31_E4AG



AW FLYER-31_N8AG



AW FLYER-33_E479



AW FLYER-33_E4B8



AW FLYER-33_E4V6



AW FLYER-33_N8E2-1

All our designs are registered and protected against unauthorized copying.


AW.FLYER



AW FLYER-33_N8E2



AW FLYER-33_N8AG



AW FLYER-33_E4K1-1



AW FLYER-33_E4K1

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-H	Design Name	AW.FLYER 31		
End-Use		Width (±2cm)	140 cm (55")	Weight	388 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A	4/5	
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	53	45
Tensile Strength	EN ISO 13934-1	864	741
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-K	Design Name	AW.FLYER 33		
End-Use		Width (±2cm)	140 cm (55")	Weight	351 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A	4/5	
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	58	31
Tensile Strength	EN ISO 13934-1	905	538
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)		

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		