AW.FLYER(Group3)

Seating Fabrics

kreateplus.com

KREATE+

designed by technology

OUR STORY

KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS

AW.FLYER



AW FLYER-35_N8J5



AW FLYER-35_N845



AW FLYER-36_N8V4



AW FLYER-36_N8W4



AW FLYER-37_N8V4



AW FLYER-37_N8W4



AW FLYER-38_N839



AW FLYER-38_N844



AW FLYER-39_N8BT



AW FLYER-39_N8G1

All our designs are registered and protected against unauthorized copying.

AW.FLYER



AW FLYER-40_N8J5



AW FLYER-40_N8V4



AW-FLYER-41_N8E4



AW-FLYER-41_N868

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-L	Design Name	AW.FLYER 35		
End-Use	AVIATION FABRICS	Width (±2cm)	140 cm (55")	Weight	467 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	50	40
Tensile Strength	EN ISO 13934-1	800	500
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-M	Design Name	AW.FLYER 37		
End-Use	AVIATION FABRICS	Width (±2cm)	140 cm (55")	Weight	412 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	57	62
Tensile Strength	EN ISO 13934-1	789	718
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4	3/4

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-N	Design Name	AW.FLYER 39		
End-Use	AVIATION FABRICS	Width (±2cm)	140 cm (55")	Weight	415 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	110	70
Tensile Strength	EN ISO 13934-1	787	727
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4	3/4

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-P	Design Name	AW.FLYER 40		
End-Use	AVIATION FABRICS	Width (±2cm)	140 cm (55")	Weight	383 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	57	76
Tensile Strength	EN ISO 13934-1	815	604
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4	3/4

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

GENERAL FABRIC INFORMATION					
Quality Name	AW.FLYER-S	Design Name	AW.FLYER 41		
End-Use	AVIATION FABRICS	Width (±2cm)	140 cm (55")	Weight	476 gr/mt²
Composition	%90 WO %10 PA	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	20000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2		
Tear Strength	EN ISO 13937-3	78	170
Tensile Strength	EN ISO 13934-1	810	846
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4	3/4

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Far Testi	FAR 25.853(a) ABD 0031 or BMS 8-236	PASS
TSE No	FAR 25.853(a) ABD 0031 or BMS 8-236	
TSE Tarihi	FAR 25.853(a) ABD 0031 or BMS 8-236	

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		