KREATE®

designed by technology

FUN FR

INHERENT CIGARETTE & MATCH

Map links




FUN FR
A119DG




FUN FR
A1G4DM



FUN FR
91G419



FUN FR
91G4Z8



FUN FR
A1AGZ8



FUN FR
9193AG



FUN FR
A1AGZ3



FUN FR
A1Z3G4



FUN FR
9169Z3

designed by technology

GENERAL FABRIC INFORMATION					
Quality Name	OREGON-B8	Design Name	FUN FR		
End-Use	CONTRACT - INHERENT FR	Width (±2cm)	140 cm (55")	Weight	502 gr/mt²
Composition	%75 RPET FR %25 FR PES	Specials			

PHYSICAL TESTS			
Test	Standarts	Results	
Abrasion End	EN ISO 12947-2	> 50000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	5	
Brush Pilling	D3511-99A	4/5	
Test	Standarts	Warp	Weft
Seam Slippage	EN ISO 13936-2	2.8	3
Tear Strength	EN ISO 13937-3	90	423
Tensile Strength	EN ISO 13934-1	1420	1148
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)		
Colour Fastness Light	EN ISO 105-B04		

FLAMMABILITY TESTS		
Test	Standarts	Results
Cigarette Test	BS 5852 PART 1 SOURCE 0	PASS
Match Testi	BS 5852 PART 1 SOURCE 1	PASS
Cigarette Test	EN 1021-1	PASS
Match Testi	EN 1021-2	PASS
Cigarette-Match Test	IMO PART 8	PASS
Cigarette-Match Test	BS 7176 LOW HAZARD	PASS
Cigarette Test	CALL 117	PASS
Cigarette Test	NFPA 260	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	Standarts	Results

CARE CODES			
Washable	Wash 30°C gentle cycle	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

OEKO TEX® STANDARD 100 2106125 Centexbel · Global Recycled Standard Certified by USB Cert. USB TEX2701 · EU Ecolabel · AS 9100 · MED MODULE D

ISO 9001:2015 · ISO 14001:2015 · ISO 45001:2018 · ISO 50001:2018 · Sedex