KREATE®

designed by technology

LUDA 09M

Map links



LUDA 09M
10A3



LUDA 09M
W209



LUDA 09M
B8B8



LUDA 09M
V5B1



LUDA 09M
B165



LUDA 09M
V5BG



LUDA 09M
Q1H5



LUDA 09M
5004



LUDA 09M
L5DB



LUDA 09M
1363



LUDA 09M
X463



LUDA 09M
D9D7


designed by technology

GENERAL FABRIC INFORMATION					
Quality Name	LUDA-B1	Design Name	LUDA 09M		
End-Use		Width (±2cm)	140 cm (55")	Weight	340 gr/mt²
Composition	%35 CV %15 LN %30 RPET %20 PES	Specials			

PHYSICAL TESTS			
Test	Standarts	Results	
Abrasion End	EN ISO 12947-2	80000	
Wyzenbeek	ASTM D4157	* 50000	
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	4	
Brush Pilling	D3511-99A		
Test	Standarts	Warp	Weft
Seam Slippage	EN ISO 13936-2	3.5	3
Tear Strength	EN ISO 13937-3	217	160
Tensile Strength	EN ISO 13934-1	1250	750
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5
Colour Fastness Light	EN ISO 105-B04		

FLAMMABILITY TESTS		
Test	Standarts	Results
Cigarette Test	BS 5852 PART 1 SOURCE 0	PASS
Cigarette Test	EN 1021-1	PASS
Cigarette Test	CALL 117	PASS
Cigarette Test	NFPA 260	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	Standarts	Results

CARE CODES			
Washable	Wash 30°C gentle cycle	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

OEKO TEX® STANDARD 100 2106125 Centexbel · Global Recycled Standard Certified by USB Cert. USB TEX2701 · EU Ecolabel · AS 9100 · MED MODULE D

ISO 9001:2015 · ISO 14001:2015 · ISO 45001:2018 · ISO 50001:2018 · Sedex