KREATE®

designed by technology

MESSINA 88

Map links



MESSINA 88
A674



MESSINA 88
10A2



MESSINA 88
84R4



MESSINA 88
81B2



MESSINA 88
G326



MESSINA 88
G2J5



MESSINA 88
G3GD



MESSINA 88
84B8



MESSINA 88
07BR



MESSINA 88
0749



MESSINA 88
0557



MESSINA 88
42T7



MESSINA 88
35L6



MESSINA 88
16H6



MESSINA 88
30W5



MESSINA 88
0232


designed by technology

GENERAL FABRIC INFORMATION					
Quality Name	MESSINA-B5	Design Name	MESSINA 88		
End-Use	UPHOLSTERY FABRICS	Width (±2cm)	143 cm (56")	Weight	481 gr/mt²
Composition	%64 PAN %36 PES	Specials			

PHYSICAL TESTS			
Test	Standarts	Results	
Abrasion End	EN ISO 12947-2	45000	
Wyzenbeek	ASTM D4157	* 50000	
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	4/5	
Brush Pilling	D3511-99A	5	
Test	Standarts	Warp	Weft
Seam Slippage	EN ISO 13936-2	2.5	3
Tear Strength	EN ISO 13937-3	118	84
Tensile Strength	EN ISO 13934-1	2071	733
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5
Colour Fastness Light	EN ISO 105-B04		

FLAMMABILITY TESTS		
Test	Standarts	Results
Cigarette Test	BS 5852 PART 1 SOURCE 0	PASS
Cigarette Test	EN 1021-1	PASS
Cigarette Test	CALL 117	PASS
Cigarette Test	NFPA 260	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	Standarts	Results

CARE CODES			
Washable	Wash 30°C gentle cycle	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		

OEKO TEX® STANDARD 100 2106125 Centexbel · Global Recycled Standard Certified by USB Cert. USB TEX2701 · EU Ecolabel · AS 9100 · MED MODULE D

ISO 9001:2015 · ISO 14001:2015 · ISO 45001:2018 · ISO 50001:2018 · Sedex