BS.BASE

Polyester Flatweave (Chenille)

kreateplus.com

KREATE+


designed by technology

OUR STORY

KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS

/kreateplus

BS.BASE




BS BASE-01_24B3Q6



BS BASE-01_24B348



BS BASE-01_24F732



BS BASE-01_24N8B3



BS BASE-01_24N8BH



BS BASE-01_24T1N2



BS BASE-01_24T1N8



BS BASE-01_24T148



BS BASE-01_2448E2



BS BASE-01_2458E2

All our designs are registered and protected against unauthorized copying.

BS.BASE



BS BASE-01_2458F7



BS BASE-01_2458N8



BS BASE-01_245848

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	BS.BASE-A	Design Name	BS.BASE 01		
End-Use		Width (±2cm)	140 cm (55")	Weight	491 gr/mt²
Composition	%100 PES	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	85000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2		
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2	2.3	2.2
Tear Strength	EN ISO 13937-3		
Tensile Strength	EN ISO 13934-1	1621	975
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Annex 6 Horizontal Burning	ECE R.118 03	PASS
Annex 7 Melting	ECE R.118 03	PASS
Annex 8 Vertical Burning	ECE R.118 03	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		