BS.RC.MAURE

Recycled Polyester Flatweave (Chenille)

kreateplus.com

KREATE+


designed by technology

OUR STORY

KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS

/kreateplus

BS.RC.MAURE



BS.RC.MAURE 01-24BH31



BS.RC.MAURE 01-24E2H9



BS.RC.MAURE 01-24E228



BS.RC.MAURE 01-2448K2



BS.RC.MAURE 02-24BH31



BS.RC.MAURE 02-24E2H9



BS.RC.MAURE 02-24E228



BS.RC.MAURE 02-2448K2

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	BS.RC.MAURE-A	Design Name	BS.RC.MAURE 02		
End-Use	BUS & COACH FABRICS	Width (±2cm)	140 cm (55")	Weight	518 gr/mt²
Composition	%45 RPET %55 PES	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	65000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	5	
Brush Pilling	D3511-99A	4/5	
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2	2	2.2
Tear Strength	EN ISO 13937-3	115	76
Tensile Strength	EN ISO 13934-1	1450	1557
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5
Colour Fastness Light	EN ISO 105-B04		

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Cigarette Test	BS 5852 PART 1 SOURCE 0	PASS
Cigarette Test	EN 1021-1	PASS
Cigarette Test	CALL 117	PASS
Cigarette Test	NFPA 260	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**

CARE CODES			
Washable	Wash 30°C gentle cycle	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Dry-cleaning in perchloroethylene gentle cycle		