ECOSTAR VELOUR

Recycled Polyester Velvet (Kdk Yarn)

kreateplus.com

KREATE+


designed by technology

OUR STORY


KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS

/kreateplus

ECOSTAR VELOUR




ECOSTAR-01_BCAD24M324



ECOSTAR-03_BAD24M324




ECOSTAR-05_BAD24M324



ECOSTAR-06_BDC24M324




ECOSTAR-08_BCAD24M324




ECOSTAR-10_BCDA24M324



ECOSTAR-11_BAD24M324



ECOSTAR-12_CBDA24M324



ECOSTAR-13_BCD24M324




ECOSTAR-14_BCD24M324

All our designs are registered and protected against unauthorized copying.


ECOSTAR VELOUR




ECOSTAR 16_CBD24M724




ECOSTAR 17_CBD24M724




ECOSTAR 22_CBD24M724



ECOSTAR 23_CBD24M724



ECOSTAR 26_CBD24M724




ECOSTAR 28_BCAD24M724




ECOSTAR 20_CBD24M724



ECOSTAR 27_CAD24M724



ECOSTAR 29_DC24M724



ECOSTAR 33_BAD24M724

All our designs are registered and protected against unauthorized copying.


ECOSTAR VELOUR



ECOSTAR 35_CABD24M724




ECOSTAR 36_CBAD24M724



ECOSTAR 37_CBDA24M724



ECOSTAR 18_CBD24M724




ECOSTAR 19_CBD24M724



ECOSTAR 21_BCD24M724




ECOSTAR 25_CBD24M724



ECOSTAR 32_ABD24M724



ECOSTAR 34_CBAD24M724



ECOSTAR 15_CAD24M724

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	ECOSTAR VELOUR-A	Design Name	ECOSTAR 03		
End-Use		Width (±2cm)	154 cm (61")	Weight	590 gr/mt²
Composition	%52 RPET %48 PES	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	100000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	5	
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2	2	2
Tear Strength	EN ISO 13937-3	45	40
Tensile Strength	EN ISO 13934-1	950	1010
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Annex 6 Horizontal Burning	ECE R.118 03	PASS
Annex 7 Melting	ECE R.118 03	PASS
Annex 8 Vertical Burning	ECE R.118 03	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Do not dry clean		