MASTER VELOUR

Polyester Velvet

kreateplus.com

KREATE+


designed by technology

OUR STORY

KREATE+ IS A TEXTILE-DESIGN AND TECHNOLOGY COMPANY THAT IS PASSIONATELY FOCUSED ON CREATING CUSTOMISED, HIGH QUALITY AND INNOVATIVE TEXTILE SOLUTIONS FOR A SUSTAINABLE FUTURE THAT ADD EXCEPTIONAL VALUE TO YOUR BUSINESS

/kreateplus

MASTER VELOUR



MASTER KOMBIN-01_BC24R824



MASTER KOMBIN-01_BC24R924




MASTER KOMBIN-01_BC24S124



MASTER KOMBIN-01_CB24S124



MASTER KOMBIN-01_CD24R924



MASTER-39_BC24R924



MASTER-39_CD24R924



MASTER-54_BC24R824



MASTER-54_BC24R924



MASTER-54_CB24S124

All our designs are registered and protected against unauthorized copying.

MASTER VELOUR



MASTER-55_BC24R824



MASTER-55_CB24R824



MASTER-56_CD24R924



MASTER-57_CB24R924



MASTER-57_CB24S124



MASTER-58_BC24R924



MASTER-58_CD24S124



MASTER-58_DC24R924

All our designs are registered and protected against unauthorized copying.

GENERAL FABRIC INFORMATION					
Quality Name	MASTER VELOUR-B	Design Name	MASTER 63		
End-Use	BUS & COACH FABRICS	Width (±2cm)	154 cm (61")	Weight	590 gr/mt²
Composition	%100 PES	Specials			

PHYSICAL TESTS			
Test	**Standarts**	**Results**	
Abrasion End	EN ISO 12947-2	100000	
Wyzenbeek	ASTM D4157		
Martindale-Pilling 2.000 Cycle	EN ISO 12945-2	5	
Brush Pilling	D3511-99A		
Test	**Standarts**	**Warp**	**Weft**
Seam Slippage	EN ISO 13936-2	2	2
Tear Strength	EN ISO 13937-3	80	40
Tensile Strength	EN ISO 13934-1	1200	700
Colour Fastness Rubbing	EN ISO 105-X12(Dry/Wet)	4/5	4/5

FLAMMABILITY TESTS		
Test	**Standarts**	**Results**
Annex 6 Horizontal Burning	ECE R.118 03	PASS
Annex 7 Melting	ECE R.118 03	PASS
Annex 8 Vertical Burning	ECE R.118 03	PASS

REPELLENCY / CLEANABILITY TESTS		
Test	**Standarts**	**Results**
Antibacterial Test	ASTM E 2149-13	85
Antiviral Test	ISO 18184	90.00
Bleach Cleanable Test	AATCC 101-ACT TM1 With Extra Process	PASS

CARE CODES			
Washable	Do not wash	Care symbols	
Iron	Low iron at max 110°C		
Tumble dry	Do not tumble dry		
Bleach	Do not bleach		
Dry clean P	Do not dry clean		